

Isolocork Filler - specs

Product Identification	Natural cork
Description	Cork based coating for in and outdoor applications.
Appearance	Viscous appearance - paste
Color	Ral colors available
Density	0,82 +/- 0,20 g/cm3
Storage	12 months in original packaging in dry place and protected from the sun
Drying time	4 to 6 hours between coats 12 to 24 hours final drying
Yield	650 grams/coat
Application Temperature	5°C to 30°C
Thermal Condutivity	0,061 W/m.K ISO 8301:1991
Water vapor permeability	2,97 EN ISO 7783:2011
Accelerated aging	Adapted to the ASTM G 53 norm
Flexion strain rupture	3.15 Mpa
Compression strain rupture	6.5 Mpa
Water absorption coefficient	0,1 kg/(m2,min0.5)
Adhension ceramic brick	0,4 N/mm2
Adhension cement block	0,6 N/mm2